



# SHRINK WRAP

 *Flame Retardant*

- Painting Containment
- Weather Protection
- Asbestos Containmentment
- Jobsite Protection
- Construction Enclosures
- Shelters



## PHYSICAL DATA

Material Composition ..... Polyethylene  
 Color ..... Opaque White  
 Denier ..... 600 gr/sqm  
 Thickness ..... 9mil & 12 mil  
(ASTM D-374)  
 Flame Retardant ..... Meets   
(meets NFPA 701: 1999, Test 2 Flammability)

## SPECIFICATIONS

	9 MIL	12 MIL
<b>Tensile Properties - Yield</b> (md/cd) p.s.i.:	1400/1200	1400/1200
<b>Break</b> (md/cd) p.s.i.:	2500/2400	2500/2400
<b>Elongation</b> (md/cd) p.s.i.:	600/700	600/700
<b>Dart Impact Grams</b> ..... <small>(ASTM D-1709)</small>	750	900
<b>U.V. Inhibitors</b> .....	5%	5%
<b>Elemendorf Tear Grams</b> (md/cd) ..... <small>(ASTM D-1922)</small>	1200/1500	1700/2800
<b>Shrink Temperature</b> ..... <small>(ASTM D-2732)</small>	300° F	300° F

To the best of our knowledge, these are typical property values & are intended as guides only, not as specification limits. Eagle Industries of Louisiana, Inc. makes no warranties as to the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations, & disclaims all liability for resulting loss or damage.



800.CONTAIN • 800.266.8246  
[www.eagleind.com](http://www.eagleind.com)

Revised 05/2008